

**KINBA SPUN**

(100% Polyester )

Kind	Composition	Length	Tenacity (N)	Elongation (%)
# 120	80/1x2(Z)	10000m	4.5	15
# 100	60/1x2(Z)	10000m	6.0	15
# 80	80/1x3(Z)	3000m	7.4	16
# 60	60/1x3(Z)	3000m	9.8	17
# 50	50/1x3(Z)	5000m	12.8	18
# 50	50/1x3(Z)	3000m	12.8	18
# 30	30/1x3(Z)	5000m	20.8	18
# 30	30/1x3(Z)	3000m	20.8	18
# 20	20/1x3(Z)	4000m	33.3	19
# 8	20/1x4(Z)	3000m	44.1	19

The data shown here represents the average results of product testing performed by Azuma.