

KINBA VINYLON

(100% Vinyon)

Kind	Composition	Length	Tenacity (N)	Elongation (%)
# 40	34/1x2(Z)	5000m	16.5	15
# 30	20/1x2(Z)	5000m	23.5	16
# 20	20/1x3(Z)	4000m	35.3	16
# 8	20/1x4(Z)	3000m	47.5	17
# 5	20/2x3(Z)	1000m	68.7	18

The data shown here represents
the average results of product
testing performed by Azuma.