

K . P . F .

(100% Polyester)

Kind	Composition	Length	Tenacity (N)	Elongation (%)
# 40	110/1x3(Z)	2000m	20.5	23
# 30	167/1x3(Z)	2000m	31.5	23
# 20	260/1x3(Z)	2000m	49.5	24
# 8	167/2x3(Z)	1000m	63.1	25
# 5	280/2x3(Z)	1000m	106.5	25
# 1	280/3x3(Z)	500m	165.2	26
# 0	280/4x3(Z)	500m	219.8	26
# 00	280/6x3(Z)	500m	329.7	27

The data shown here represents
the average results of product
testing performed by Azuma.

JINMA-KPF

Kind	Composition	Length	Tenacity (N)	Elongation (%)
# 30	167/1x3(Z)	2000m	30.2	21
# 20	240/1x3(Z)	2000m	44.8	22
# 8	167/2x3(Z)	1000m	61.2	22

The data shown here represents
the average results of product
testing performed by Azuma.